

(9)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

**0 394 689  
A2**

(12)

**EUROPEAN PATENT APPLICATION**

(21) Application number: 90105915.4

(51) Int. Cl.<sup>5</sup>: D06M 15/643

(22) Date of filing: 28.03.90

(23) Priority: 29.03.89 US 330108

(43) Date of publication of application:  
31.10.90 Bulletin 90/44

(63) Designated Contracting States:  
AT BE CH DE ES FR GB GR IT LI LU NL SE

(71) Applicant: UNION CARBIDE CHEMICALS AND  
PLASTICS COMPANY, INC.  
39 Old Ridgebury Road  
Danbury Connecticut 06817-0001(US)

(72) Inventor: Sabla, Angelo James  
1370 Edcris Road  
Yorktown, New York, 10598(US)  
Inventor: Gum, Mary Lou  
22 Cornell Road  
New Fairfield, Connecticut, 06812(US)

(74) Representative: von Hellfeld, Axel, Dipl.-Phys.  
Dr. et al  
Wuesthoff & Wuesthoff Patent- und  
Rechtsanwälte Schweigerstrasse 2  
D-8000 München 90(DE)

(54) Method of treating fabrics and other substrates with exhaustible cationic silicones.

(57) A method of improving the softness, or antistatic properties of a textile without yellowing comprising treating said textile with a composition comprising a) about 0.05 to about 5 weight percent of a cationic silicone of the structure  $M D_x D'_y M$  where M is  $(CH_3)_3 SiO_{1/2}$ ; D is  $OSi(CH_3)_2$ ; D' is  $CH_3 SiO(CH_2)_3 OCH_2 CH(OH) CH_2 N^+(CH_3)_3 Cl^-$ ;  $x = 20-200$ ;  $y = 3-60$ ; and b) about 0 to 2 % of an electrolyte.

**EP 0 394 689 A2**